

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.


**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09D 10/00, B32B 35/00		A1	(11) International Publication Number: WO 93/23485
			(43) International Publication Date: 25 November 1993 (25.11.93)
(21) International Application Number: PCT/US93/02494		(72) Inventors; and	
(22) International Filing Date: 16 March 1993 (16.03.93)		(75) Inventors/Applicants (for US only) : MATZ, Gary, F. [US/US]; 207 Alden Road, Rosslyn Farms, PA 15106 (US). SANBORN, Kimberly, Borelli [US/US]; 30 Sheri Lane, South Weymouth, MA 02190 (US).	
(30) Priority data: 885,514 19 May 1992 (19.05.92) US		(74) Agents: HANDELMAN, Joseph, H. et al.; Ladas & Parry, 26 West 61 Street, New York, NY 10023 (US).	
(60) Parent Application or Grant (63) Related by Continuation US 885,514 (CON) Filed on 19 May 1992 (19.05.92)		(81) Designated States: AT, AU, BB, BG, BR, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, RO, RU, SD, SE, SK, UA, US, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, SN, TD, TG).	
(71) Applicant (for all designated States except US): THE GILLETTE COMPANY [US/US]; Prudential Tower Building, Boston, MA 02199 (US).		Published With international search report.	

(54) Title: CORRECTION FLUID



(57) Abstract

An aqueous, correction fluid that includes a suspending agent, a binding resin, water, and an opacifying pigment. The suspending agent is preferably a gum or hydrocolloid, e.g., xanthan gum, and the composition preferably has a shear-thinning index (n) of from about 0.08 to 0.50. The fluid may be dispensed from a pen as described in the figure or from a container. A dispenser (10) comprises elongated body member (12) and barrel (14). A tubular passage (16) extends through barrel (14) and opens rearwardly into body member (12) for flow of correction fluid from the body member into barrel (14). Within tubular passage (16) a tubular spring retainer (26) is disposed in interfitting engagement with barrel (14).

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

- 1 -

CORRECTION FLUID

This invention relates to correction fluids.

Correction fluids are used for
5 correcting handwritten, typewritten or
photocopied markings on paper. Generally,
correction fluids are applied to a paper surface
in liquid form. After application, the fluids
dry relatively quickly to provide a film which
10 can effectively cover erroneous markings on the
surface and can receive a corrected marking. It
is desired that the dried film be strongly
bonded to the paper surface, and sufficiently
flexible that the film will not be removed under
15 normal conditions. It is also desired that the
composition dry at a rapid rate. Other desired
performance characteristics include good storage
stability, and flow and viscosity
characteristics which permit easy and even
20 application of the fluid.

Correction fluids typically contain a
binding resin that provides the flexible film,
and an opacifying pigment, usually titanium
dioxide, dispersed in a solvent. It is
25 desirable, for environmental reasons, that
correction fluids include little or no volatile
organic solvents.

- 2 -

Correction fluids are often supplied in a small bottle with an applicator brush attached to the cap. Since the opacifying pigment in the fluid (typically titanium dioxide) tends to settle out over time, glass or metal mixing beads are sometimes included to help redisperse the agent, the user being instructed to shake the bottle prior to use. However, thorough shaking is commonly regarded as a nuisance, so that much of the opacifying pigment remains at the bottom of the bottle. This condition is exacerbated by evaporation of the solvent component when the bottle is open. Accordingly, much of the correction fluid in each bottle may be thrown away as the solids become increasingly difficult to redisperse.

In general, the invention features, in one aspect, an aqueous correction fluid having a shear-thinning index of between 0.08 and 0.50. The correction fluid includes a binding resin, an opacifying pigment, e.g., titanium dioxide, water, and a sufficient quantity of a suspending agent to provide the fluid with the above shear-thinning index.

The invention features, in another aspect, a correction fluid dispensing system that includes a container and a correction fluid. The container includes a chamber for holding the correction fluid, and a capping element that fits over an opening in the chamber wall. The capping element includes a brush element that extends into the chamber when the capping element covers the opening. The correction fluid includes water, an opacifying pigment, a suspending agent, and a binding resin.

The invention features, in another

- 3 -

aspect, an aqueous correction fluid, which includes a binding resin, at least 15% of an opacifying pigment, water, and a suspending agent.

5 The invention features, in another aspect, a correction fluid dispensing system including a pen having a chamber for holding a correction fluid, the chamber being defined by a wall including an opening, and a spring loaded
10 valve at said opening for controlling flow of the fluid through the opening. The dispensing system includes a correction fluid within the chamber. The correction fluid contains a binding resin, an opacifying pigment, a
15 suspending agent, and water.

 The invention features, in another aspect, a process for covering a marking on a paper. The method includes contacting an applicator with a correction fluid having a
20 shear-thinning index of between 0.08 and 0.50. The applicator may be any suitable applicator for use with fluid compositions, e.g., a brush or a pen tip. The fluid contains a binding resin, an opacifying pigment, a suspending
25 agent, and water. The contacting is done with sufficient force that some of the gelled correction fluid flows onto the applicator. The correction fluid on the application is used to cover a marking on a paper surface, and the
30 correction fluid is then allowed to dry. A corrective marking may subsequently be applied to the dried correction fluid, if desired.

 The correction fluids of the invention include a suspending agent to provide shear
35 thinning fluids, i.e., fluids which exhibit non-newtonian properties. By this, it is meant that the fluids are relatively thick at rest, and do

- 4 -

not readily flow out of a container if the container is inverted. Yet the fluids thin out when sheared, and are thus easily applied to a surface because they flow readily onto an applicator, e.g., a brush, when the applicator actively contacts the fluids. The fluids also flow readily from the applicator to a surface when the applicator is passed across the surface.

Significantly, because of the non-newtonian properties of the fluids, the opacifying pigment in the gelled correction fluids does not significantly settle over extended periods of time, eliminating or reducing the need to shake the fluid container. Advantageously, the thixotropic flow properties allow the fluids of the invention to be dispensed using a wide variety of dispensers. In particular, due to the non-settling nature and resistance to viscosity change with change in temperature of the fluid, the fluid can be dispensed from a pen dispenser without "gushing" or other problems usually encountered. Further, the fluid does not normally require shaking before use, and can be used over long periods of time without settling or drying out. In addition to the advantageous flow properties, the compositions have good drying, bonding, flexibility and storage stability characteristics.

The non-newtonian properties of the gel may be measured in terms of the shear-thinning index (n), as described, e.g., in Zgambo, U.S. Patent No. 4,786,198 ("Zgambo"), the disclosure of which is hereby incorporated by reference. For the purposes of this invention, the shear-thinning index (n) is

- 5 -

calculated by fitting shear stress (T) and shear rate values ($\dot{\gamma}$) obtained from rheological measurements on a viscometer, e.g., a HAAKE ROTOVISCO, Haake Inc., Saddle Brook, N.J., to the empirical power equation $T = K\dot{\gamma}^n$ (where K and n are calculated constants). As described in Zgambo, the shear-thinning index is obtained by measurements of an aqueous solution of the shear-thinning material at shear rates between about 30 and about 300 sec^{-1} . Shear stress values are measured from the curve on the viscometer at different shear rates (typically 30, 90, 150, 210 and 300 sec^{-1}) and the measured shear stress values are fitted to the shear rates using a curve-fitting program.

By "aqueous" it is meant that the fluid is water-based, and contains less than about 10% of volatile organic solvents.

Preferred compositions include, as the suspending agent, a gum or hydrocolloid, preferably a semi-synthetic gum, e.g. a cellulose derivative or microbial fermentation gum, more preferably xanthan gum, a titanium dioxide pigment, an acrylic polymer binder resin, and a phosphate ester dispersant. Preferably, the composition includes, by weight, about 2 to 20 percent binding resin; at least 15 percent pigment; about 0.2 to 2.0 percent dispersant; and about 0.15 to 0.6 percent suspending agent. They also include water. The drying time of preferred compositions is less than about 60 seconds; the viscosity at 40°C. is within $\pm 10\%$, preferably $\pm 5\%$, of the viscosity at 25°C.; and the shear thinning index (n) from 0.15 to 0.30. Preferred compositions have a settling value of about 10, when measured according to ASTM D869-48 (1974).

- 6 -

Other features and advantages of the invention will be apparent from the description of the preferred embodiment thereof, and from the claims.

5 The figure is of a preferred correction fluid dispensing system.

 The preferred correction fluid includes a suspending agent, a binding resin, a dispersing agent, an opacifying pigment, and
10 water.

 The flow and settling characteristics of the fluid are provided by the suspending agent. The suspending agent is dispersed in the composition to provide a correction fluid having
15 a shear-thinning index (n) of between about 0.08 to about 0.50, more preferably between about 0.10 and 0.30, and most preferably between about 0.15 to about 0.25. Too low a shear-thinning index may result in a fluid that does not have
20 sufficient flow to be easily applied; too high a shear-thinning index may result in a fluid that gushes or that exhibits settling of the pigment.

 Inclusion of the suspending agents provides correction fluids which are thickened
25 viscous liquids at rest or low shear rates. For example, compositions of the invention preferably have a viscosity of between 400 and 2000 cPs, more preferably between about 500 and 1000 cPs, at a shear rate of 30 sec^{-1} . However,
30 in response to the high shear rates encountered during application of the composition, e.g., by brushing, the compositions undergo shear-thinning and have an estimated viscosity of less than about 5 cPs (obtained by extrapolation from
35 the log curves of shear rate and shear stress).

 The preferred fluids also do not undergo a significant change in viscosity in

- 7 -

response to temperature. Particularly preferred fluids are those in which the viscosity at 40°C. is within $\pm 10\%$, preferably $\pm 5\%$, of the viscosity at 25°C.

5 The preferred suspending agents are gums or hydrocolloids. The gums or hydrocolloids may be natural gums such as plant exudates, e.g., tragacanth, seaweed extracts, e.g., carrageenan, and alginates. The gums can
10 also be semi-synthetic gums such as cellulose derivatives, e.g., carboxymethylcellulose, guar and locust bean gum, and hydroxyethylcellulose, or microbial fermentation gums, e.g., as xanthan gum. Xanthan gum is a particularly preferred
15 suspending agent. Preferred grades of xanthan gum are available under the tradenames KELZAN M, KELZAN S, and KELTROL, commercially available from The Kelco Company. KELZAN S and KELTROL are easier to disperse, requiring less agitation
20 than KELZAN M.

 The amount of suspending agent included in the composition can vary, depending on the flow properties desired and the other components selected. It is preferred that a
25 sufficient quantity of the suspending agent be included to provide a viscosity of from about 500 to 1000 cPs at a shear rate of 30 sec^{-1} , and a viscosity of from about 60 to 130 cPs at a shear rate of 300 sec^{-1} . Typically, the
30 correction fluids contain, by weight, about 0.15 to 0.6 percent of the suspending agent, preferably about 0.20 to 0.50 percent.

 The binding resin may be any polymeric or monomeric resin which is capable of binding
35 the pigment component to provide, after drying of the correction fluid, a dry, coalesced residue which is substantially water insoluble.

- 8 -

It is further desirable that the residue be receptive to ink, e.g. to markings rewritten over the corrected mark.

Many conventional binding resins that
5 can be used in the fluids are well-known to those skilled in the art. The preferred resins are acrylic polymers, in particular acrylic thermoset polymeric materials, sold in the form of emulsions under the trade names CARBOSET and
10 CARBOPOL by B.F. Goodrich. These preferred polymers have acid numbers below about 50, weight average molecular weights between about 15,000 and about 200,000, and glass transition temperatures between about 20°C. and about 70°C.
15 Particularly preferred polymers have acid numbers between about 25 and 30, molecular weights between about 25,000 and 35,000, and glass transition temperatures between about 25°C. and 60°C. The emulsions normally have a
20 solids level of about 35 to 60%.

Enough resin should be included in the fluid so that a consistent connective film will result, but not so much that the fluid will destabilize with time and thicken. The
25 preferred composition contain about 2 to 20 weight percent binding resin, more preferably about 5 to 15 percent, and most preferably 8 to 12 percent.

In order to ensure that a stable
30 composition is formed, i.e., to avoid flocculation, and to improve distribution of the pigment through the composition, a dispersing agent is employed. Suitable dispersing agents are those which are compatible with typewritten
35 ink. Preferred dispersing agents are polysorbitans, phosphate esters, sodium alkyl polyether sulfonates, ethoxylated alcohol, nonyl

- 9 -

phenoxy polyethylene oxide, and octyl phenoxy POE. Of these, organic phosphate esters are particularly preferred, e.g., those commercially available from GAF under the tradename GAFAC RD-510 and BG-510. It is preferred that the composition contain from about 0.2 to 2 weight percent dispersant, more preferably from 0.5 to 1.5 percent, and most preferably from 0.5 to 1.0 percent.

Any suitable opacifying pigment having adequate hiding power to cover a desired type of marking, e.g., typed or handwritten, on a paper surface, may be utilized in the compositions of the invention. Titanium dioxide is preferred, as it provides a basic white color which can be toned to meet a variety of requirements depending on the paper stock with which the correction fluid is to be employed. The grade of titanium dioxide is selected based upon the binding resin used, and the desired texture of the composition. For most applications, preferred grades of titanium dioxide are R-931, R-900 and R-901, available from E.I. DuPont de Nemours & Co., Wilmington, Delaware, and RXL, available from Tioxide, Quebec, Canada. Of these, R-931 is particularly preferred. It is preferred that the composition contain, by weight, at least 15 percent pigment, preferably about 20 to 60 percent, more preferably about 25 to 50 percent, and most preferably about 35 to 45 percent.

The amount of water in the fluid will depend upon the amount required to hydrate a given suspending agent and disperse the selected pigment. Normally, a water level of from about 35 to 65 weight percent, based on the total weight of the composition, will be suitable.

- 10 -

The amount of water required to hydrate the Xanthan gum is normally between 33 and 50 weight percent of the total amount of water in the composition. The pigment dispersion contains
5 the remaining 50 to 67 weight percent of the total amount of water in the composition.

The compositions of the invention can include other conventional ingredients. For example, chelating agents, such as sodium EDTA,
10 are normally included in the fluid in amounts between 0.1 and 1.0 percent by weight to protect any metal parts in the dispenser against metal ions present in the water. Defoamers are also normally included.

15 Preferred compositions exhibit relatively short drying times (preferably less than 60 seconds). Compositions can be tested for drying time by applying the fluid on the marking to be corrected and at 5 second
20 intervals determining the time when you can write over or type over the fluid without disturbing the surface of the corrected mark. Preferred compositions also exhibit very little settling over time. When settling is measured
25 according to ASTM D2243-68, a "no change" or "slight" rating is typically obtained. When measured by the more quantitative settling measurement method outlined in ASTM D869-48 (1974), the compositions normally are rated
30 about 8 to 10 on a scale of 1 to 10, where 10 is perfect suspension.

The fluid is preferably made in three stages.

35 First, the hydrocolloid is slowly added into approximately one third of the total amount of water to be used in the composition. This allows the hydrocolloid to be hydrated.

- 11 -

Mixing is done at a very low shear, so as not to incorporate air into the mixture. The speed is monitored and increased, producing a small vortex as the hydrocolloid dispersion thickens.

5 Next, a pigment dispersion is prepared. The pigment is added into a solution of dispersant in water at a slow rate, to prevent agglomeration, and mixed at high shear until the pigment particle size is above 7 on a
10 Hegman gage. High shear is required to break down the pigment particle size. A high speed dispersator from Ross and Sons may be used to prepare the pigment dispersion. Other equipment
15 such as a sand mill, ball mill, Eiger Mill or Gaulin can be used to obtain the desired pigment particle size.

 Last, the pigment dispersion is added slowly into the hydrocolloid solution using a low shear mixer. A small vortex is maintained
20 during this step. Once all of the pigment dispersion is added, the resin is added slowly. Additional colorant may be added to tint the fluid to the desired color.

 The following example illustrates the
25 invention.

Example

 Three correction fluid compositions (samples 1-3) were prepared according to the invention, with formulations as shown in Table
30 1. These fluids were tested against two commercially available correction fluids, available from Gillette under the tradenames JUST FOR COPIES® (control 1) and MISTAKE OUT® (control 2). Each fluid was tested for shear-
35 thinning index (n), using a HAAKE ROTOVISCO viscometer at 0 to 300 sec^{-1} shear rates, and temperature stability using the same procedure

- 12 -

at 25° and 40°C. The fluids were also tested for opacity, drying time, and flexibility and adhesion.

Opacity was measured by preparing draw
5 downs of the fluids with a 0.001" Bird Bar on
Leneta No. 18A charts. The charts have a black
and white surface which the fluid covers. A
contrast ratio measurement was made with a
colorimeter and the ratio of the black reading
10 to the white surface reading was calculated to
obtain the result.

Flexibility and adhesion is measured
by a fold test. The fluid is applied to a
marking on a paper substrate and allowed to dry.
15 The paper is then folded inwardly and creased,
and folded crosswise and creased again. The
dried correction fluid is then examined for
cracking (indicating poor flexibility) or
flaking off (indicating poor adhesion). Results
20 are expressed on a scale of 1 to 5, with 5
indicating no cracking or flaking.

The results of this testing are shown
in Table 2. The fluids exhibit very little
change in their viscosity, on the average less
25 than 5%, over the temperature change which would
typically be encountered if a fluid in a
dispenser at room temperature (25°C.) were
subjected to the heat of the hand of a user
holding the dispenser (40°C.). The fluids also
30 exhibit significantly lower shear thinning
indices (about 0.20 average) compared to the
control fluids (greater than 0.60), indicating
that the fluids will resist settling, but will
shear thin during use to an advantageously low
35 viscosity. The other properties of the fluids
are similar to those of the control fluids.

- 13 -

Table 1

<u>Ingredients</u>	<u>Vendor</u>	<u>Purpose</u>	<u>Sample</u>		
			1	2	3
Deionized Water	-----	Solvent	46.4	47.4	47.3
Sodium EDTA	W.R. Grace	Chelating agent	0.26	0.3	0.3
Kelzan M	Kelco	Suspending agent	0.22	0.3	0.4
Germeben II	Sutton Lab	Preservative	0.43	0.5	0.5
TiO ₂ R-931	Dupont	Pigment	41.50	40.0	40.0
Gafac BG-510	GAF	Dispersant	0.75	1.0	1.0
RES 3680	Unocal 76	Binder	10.43	10.5	10.5

Table 2

	<u>Sample 1</u>	<u>Sample 2</u>	<u>Sample 3</u>	<u>Control 1</u>	<u>Control 2</u>
<u>Viscosity</u>					
30 sec ⁻¹					
@ 25°C	459.5	564.2	785.5	303.8	358.1
@ 40°C	455.7	553.4	802.9	217.0	282.1
300 sec ⁻¹					
@ 25°C	70.9	97.7	130.2	166.0	176.9
@ 40°C	71.6	89.0	124.8	106.3	120.4
<u>Shear Thinning Index</u>					
@ 25°C	0.22	0.23	0.22	0.74	0.70
@ 40°C	0.20	0.20	0.19	0.70	0.63
<u>Opacity</u>	0.998	0.998	0.998	N/T	N/T
<u>Dry Time</u> (secs.)	40	45	45	N/T	N/T
<u>Flexibility/</u> <u>Adhesion</u>	5	5	5	N/T	N/T

* N/T indicates not tested.

- 15 -

The preferred correction fluids can be applied using conventional bottle and brush dispensers, rolling ball systems, or a squeeze bottle or pen. Advantageously, the flow properties of the fluids of the invention prevent gushing of the fluid when applied from a pen dispenser, a common problem with conventional fluids. Preferably, a squeeze bottle or pen is used, and a spring loaded valve will be provided to control rate of dispensing. A preferred spring loaded pen dispenser is shown in Fig. 1 and disclosed in U.S. Patent No. 5,056,949, the disclosure of which is incorporated herein by reference. When a pen dispenser is used, it is preferred that the viscosity of the fluid be from about 400 to 600 cPs measured at 30 sec⁻¹.

Referring to Fig. 1, dispenser 10 comprises elongated body member 12 and barrel 14. A tubular passage 16 extends through barrel 14 and opens rearwardly into body member 12 for flow of correction fluid from the body member into barrel 14. Tubular passage 16 has a pair of circumferential shoulders 18 and 20 adjacent the forward end thereof, and is tapered inwardly terminating at a circular rim 22 surrounding and forming an orifice 24. Within tubular passage 16, a tubular spring retainer 26 is disposed in interf itting engagement with barrel 14, tubular spring retainer 26 having an external surface providing for a force fit into tubular passage 16 such that forward surface 28 of the retainer has an outward portion contacting circumferential shoulder 18 and a portion extending radially inwarding into passage 16. Retainer 26 has an inwardly projecting portion 30 which serves to support a spring 32, the

- 16 -

spring being of a diameter to closely fit within the inner wall of tubular spring retainer 26. A socket member 34 having a plurality of axial ribs 36 is supported by spring 32 at its forward end and a spherical ball 38 is disposed between socket member 34 and circular rim 22 of passage 16. Spherical ball 38 is of larger diameter than the circular rim such that only a portion of the ball extends beyond orifice 24 with the outer surface of the ball forming a seal when contacting circular rim 22.

An alternative correction fluid dispersing system includes a container for storing one of the preferred correction fluids. The container includes a chamber, which is defined by a cylindrical wall. A cap fits over an opening in the wall. The cap includes a brush portion that extends into the chamber. In use, as the brush is moved through the correction fluid, the fluid that contacts the brush is exposed to relatively high shear and flows onto the brush. The fluid on the brush again thickens, and remains thickened until brushed across a marking on paper. The shear force of the fluid contacting the paper causes the fluid to shear thin and flow onto the paper, covering the marking. Once dry, a corrective marking can be applied.

Other embodiments are within the claims.

- 17 -

C L A I M S

1. An aqueous correction fluid having a shear-thinning index of between 0.08 and 0.50, said correction fluid comprising a binding
5 resin, an opacifying pigment, water, and a sufficient quantity of a suspending agent to provide said fluid with said shear-thinning index.
2. A composition of claim 1, wherein the
10 suspending agent is a gum or hydrocolloid.
3. A composition of claim 2, wherein the dispersing agent is a semi-synthetic gum.
4. A composition of claim 3, wherein the semi-synthetic gum is a cellulose derivative or
15 microbial fermentation gum.
5. A composition of claim 4, wherein the semi-synthetic gum is xanthan gum.
6. A composition of claim 1, wherein the binding resin is an acrylic polymer.
- 20 7. A composition of claim 1, wherein the pigment is titanium dioxide.
8. A composition of claim 1, further comprising a dispersing agent.
9. A composition of claim 8, wherein the
25 dispersing agent is a phosphate ester.
10. A composition of claim 1, comprising about 2 to 20 percent binding resin, about 20 to 60 percent pigment, about 35 to 65 percent water and about 0.1 to 0.6 percent suspending agent.
- 30 11. A composition of claim 10, further comprising about 0.2 to 2.0 percent dispersing agent.
12. A composition of claim 1, having a settling value of about 10.
- 35 13. A composition of claim 1, having a drying time less than about 60 Seconds.
14. A composition of claim 1, having a

- 18 -

viscosity at 40°C. which is within $\pm 10\%$ of its viscosity at 25°C.

15. A composition of claim 1, having a shear-thinning index (n) of from about 0.10
5 to 0.30.

16. A correction fluid dispensing system,
comprising
a container comprising
a chamber for holding a
10 correction fluid, said chamber being defined by a wall including an opening, and
a capping element covering said opening, said capping element comprising a brush element extending into said chamber when said
15 capping element covers said opening; and
a correction fluid within said chamber, said correction fluid comprising a binding resin, an opacifying pigment, a suspending agent, and water.

20 17. A dispensing system of claim 16, wherein the suspending agent is a gum or hydrocolloid.

18. A dispensing system of claim 17,
wherein the dispersing agent is a semi-synthetic
25 gum.

19. A dispensing system of claim 18,
wherein the semi-synthetic gum is a cellulose derivative or microbial fermentation gum.

20. A dispensing system of claim 19,
30 wherein the semi-synthetic gum is xanthan gum.

21. A dispensing system of claim 16,
wherein the opacifying pigment is titanium dioxide.

22. A dispensing system of claim 16,
35 wherein said correction fluid further comprises a dispersing agent.

23. A dispensing system of claim 16,

- 19 -

wherein said correction fluid comprises about 2 to 20 percent by weight binding resin, about 20 to 60 percent by weight pigment, about 35 to 65 percent by weight water and about 0.1 to 0.6 percent by weight suspending agent.

24. A dispensing system of claim 16, wherein said correction fluid has a settling value of about 10.

25. A dispensing system of claim 16, wherein said correction fluid has a drying time less than about 60 seconds.

26. A dispensing system of claim 16, wherein said correction fluid has a viscosity at 40°C. which is within $\pm 10\%$ of its viscosity at 25°C.

27. A dispensing system of claim 16, wherein said correction fluid has a shear-thinning index (n) of from about 0.08 to 0.50.

28. A dispensing system of claim 27, wherein said correction fluid has a shear-thinning index (n) of from about 0.10 to 0.30.

29. An aqueous correction fluid comprising a binding resin, at least 15% of an opacifying pigment, water, and a suspending agent.

30. A fluid of claim 29, wherein said opacifying agent is titanium dioxide.

31. A fluid of claim 29, wherein said fluid has a shear-thinning index of between about 0.08 and 0.50.

32. A correction fluid dispensing system comprising:

a pen having a chamber for holding a

a wall including an opening, and a spring loaded valve at said opening for controlling flow of said fluid through said opening; and a correction fluid within said

BEST AVAILABLE COPY

- 20 -

chamber, said correction fluid comprising a binding resin, an opacifying pigment, a suspending agent, and water.

33. A dispensing system of claim 32,

5 wherein said fluid has a shear thinning index of between about 0.08 and 0.50.

34. A dispensing system of claim 32,

wherein the dispersing agent is a semi-synthetic gum.

10 35. A dispensing system of claim 32,

wherein the semi-synthetic gum is a cellulose derivative or microbial fermentation gum.

36. A dispensing system of claim 32,

wherein the semi-synthetic gum is xanthan gum.

15 37. A process for covering a marking on a paper, comprising the steps of

contacting an applicator with a gelled correction fluid comprising a binder resin, an opacifying pigment, a suspending agent and
20 water, said correction fluid having a shear thinning index of between 0.08 and 0.50, with sufficient force that some of said correction fluid flows onto said applicator,

covering a marking on a paper surface
25 with the correction fluid that is on said applicator; and

allowing said correction fluid covering said marking to dry.

38. A process of claim 37, further

30 comprising the step of applying a corrective marking to the surface of the dried correction fluid.




Fig. 1

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US93/02494

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :C09D 10/00; B32B 35/00
 US CL :106/20A, 523/161; 427/140, 260, 261, 288

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 106/20A, 523/161; 427/140, 260, 261, 288

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

Please See Extra Sheet.

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US, A, 4,686,246 (Gajria) 11 August 1987 Col. 2, lines 56-57, col. 3, line 27, col. 4, lines 4, 5, 25, 30, col. 5, lines 10-15 and examples I, II and III.	1-6, 8, 10, 11-15, 29-31
X	US, A, 4,786,198 (Zgambo) 22 November 1988 See claims 1-19, col. 3 and 4, example III.	1-6, 8 and 12-15
X	US, A, 4,971,628 (Loftin) 20 November 1990 See col. 3-5, especially col. 3, line 7 and col. 5, lines 45-65	1-5, 8-9, 12-14
X	US, A, 4,329,448 (Cox et al) 11 May 1982 See column 22 including example 17.	1-4, 6-8, 10-15, 29-31

☒ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	* T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
* A		document defining the general state of the art which is not considered to be part of particular relevance
* E		earlier document published on or after the international filing date
* L		document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
* O		document referring to an oral disclosure, use, exhibition or other means
* P		document published prior to the international filing date but later than the priority date claimed
	* X	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
	* Y	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
	* A	document member of the same patent family

Date of the actual completion of the international search

03 MAY 1993

Date of mailing of the international search report

18 JUN 1993

Name and mailing address of the ISA/US
 Commissioner of Patents and Trademarks
 Box PCT
 Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

MARGARET EINSMANN GUYEN NGOC-HO

Telephone No. (703) 308-3826

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US93/02494

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP, A, 1-261473 (Tombow Enpitsukk) 18 October 1989 See Abstract.	1, 7, 8, 29-31, 37, 38
X	JP, A, 2-199180 (Pentel KK) 02 August 1990 See Abstract	29-30, 37-38
X	DE, A, 3,919,588 (Kores Holding Zug) 21 December 1989 See Abstract	1, 6-8, 29-31, 37-38
X	SU, A, 891730 (Mosc. Chem. Ind. Res.) 23 December 1981 See Abstract	1, 6-10, 29-31, 37-38

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US93/02494

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:
(Telephone Practice)
Please See Extra Sheet.

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:
1-15, 29-31 and 37-38

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US93/02494

B. FIELDS SEARCHED

Electronic data bases consulted (Name of data base and where practicable terms used):

APS: CORRECTION

GUM

ACRYLIC

WATER OR H₂O

TITANIUM DIOXIDE

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

Group I, claims 1-15, 29-31 and 37-38 C09D 10/00

Group II, claims 16-28

A46B 11/00

Group III claims 32-36

B43M 11/06

Group I is a composition and process of using it. Group I (composition claims) is related to Group II as intermediate final product. Group I is related to Group III as intermediate final product. The intermediate can be used to make separate and distinct final products, each final and the intermediate being distinct.